

# ESCANABA

thickness: 1.1-1.3MM  
average size: 55 sq. ft  
availability: 3-4 Weeks  
category: Protected  
finish type: Pebbled  
raw material: European  
Made in Italy

Escanaba was developed for aviation but is a beautiful option for high traffic areas in any type of project. A smooth and consistent small pebble grain gives an elegant and clean upholstered finish. Fully treated in the drum, it passes stringent aviation flammability requirements. Standard colors delivered in 3-4 weeks and custom colors available in 4-5 weeks after approved strike-off.

**Colorways available:** Battleship, Beige, Cappuccino, Chambray, Charcoal, Espresso, Lake Effect, Light Taupe, Motown, Mushroom, Pearl, Sandpoint, and Smoke Grey

## SPECIFICATIONS

### performance characteristics

### PERFORMANCE LEATHER

<b>EN ISO 4045</b>	
DETERMINE Ph & Ph (DIFFERENCE FIGURE)	Min 3,2
<b>ISO105/B02</b>	
COLOR FASTNESS OF LEATHER TO LIGHT: XENON LAMP	Grey Scale ≥ 3 on specimen Grey Scale = 3 on Reference Blue Wool #5
<b>EN ISO 15700</b>	
COLOR FASTNESS TO WATER SPOTTING	Grey Scale ≥ 3 (No permanent swelling)
<b>ISO 11641</b>	
COLOR FASTNESS OF LEATHER TO PERSPIRATION	80 Cycles ≥ 3.5
<b>EN ISO 11640</b>	
COLOR FASTNESS OF LEATHER TO RUBBING	500 Cycles Dry ≥ 4 250 Cycles Wet ≥ 3.5
<b>EN ISO 11644</b>	
FINISH ADHESION	3 N/cm
<b>EN ISO 3376</b>	
MEASURE TENSILE STRENGTH AND % ELONGATION	Tensile Strength ≥ 8 Mpa % Elongation ≤ 80%
<b>EN ISO 5402</b>	
FLEXING ENDURANCE (FLEXOMETER METHOD)	50,000 Cycles (no finish damage cracks)
<b>EN ISO 17233</b>	
COLD CRACK RESISTANCE OF FINISH	-15°C (no finish cracks)
<b>EN ISO 3377-1</b>	
TEAR STRENGTH (SINGLE EDGE TEAR)	>20 N Minimum

### flame resistance

CA TB 117 - 2013	Complies
NFPA - 260 CIGARETTE IGNITION	Class 1
FMVSS 302	Complies
FAR 25.853 (a)	
(1) (ii) 12 Seconds	Complies
FAR 25.853 (a).	
(1) (ii) 60 Seconds	Complies

